

# DATA SHEET TYPE II



## DESCRIPTION

### Type II

Expanded polystyrene sheets produced in various sizes to suit multiple needs and/or uses.

## PRODUCT DATA

### Dimensions

According to your needs.

## EVALUATION

- > Certified INTERTEK ETL SEMKO
- > Conforms to CAN/ULC-S701-01 standards
- > CCMC #12836-L

PHYSICAL PROPERTIES	IMPERIAL	METRIC	ASTM TEST	EPS TYPE 2
<b>Thermal resistance:</b> R-value at 75°F (24°C) for 1 in (25 mm) thickness	$\frac{\text{hr.ft}^2\text{°F}}{\text{BTU}}$	$\frac{\text{m}^2\text{°C}}{\text{W}}$	C-518 C-177	4.0 min. (0.70 min.)
Compressive strength (min.) at 10% distortion	psi	(kPa)	D-1621	16 (110)
Bending strength (min.)	psi	(kPa)	C-203	35 (240)
<b>Dimensional stability:</b> % of linear change (max.)	%	%	D-2126	1.5
Coefficient of thermal expansion (max.)	in/in/°F	(mm/mm/°C)	D-696	$3.5 \times 10^{-5}$ ( $6 \times 10^{-5} \text{C}^{-1}$ )
Water vapor permeability (max.)	Perm-inch	(ng/Pa.s.m <sup>2</sup> )	E-96	3.5 (200)
Water absorption (max.)	%	%	D-2842	4
<b>Effective temperature range:</b> > Continuous > Intermittent	°F °F	(°C) (°C)	- -	167 (75) 180 (82.2)
Flame spread rating	-	-	(CAN/ULC S102.2 M)	< 140
Smoke developed	-	-	(CAN/ULC S102.2 M)	< 380
Capillarity	-	-	-	Nil

## VALEUR ISOLANTE PERMANENTE GARANTIE

The thermal resistance of this type of insulation is permanent due to its cellular structure which contains only stabilized trapped air. EPS performance does not diminish over time.

## ECOLOGICAL

Contains no CFCs or HCFCs.

## NOTES

EPS beads should be considered flammable when subjected to a source of intense heat or a constant strong flame. They are vulnerable to petroleum-based solvents and prolonged exposure to ultraviolet radiation. EPS must therefore be covered according to the National Building Code.